



QUALITY ASSURANCE SPECIFICATIONS™

SFI SPECIFICATION 36.2

DISCONTINUED: JUNE 5, 2019*

PRODUCT: Drag Boat Capsule Canopy Material

1.0 GENERAL INFORMATION

- 1.1 This SFI Specification establishes uniform test procedures and minimum standards for evaluating and determining performance capabilities for Drag Boat Capsule Canopy Material used by individuals engaged in competitive motorsports.
- 1.2 The procedures, test evaluations and standards contained herein, are intended only as minimum guidelines for construction and evaluation of products. Certification that products meet such minimum standards is made by the product manufacturer and products are not certified, endorsed or approved by SFI under this program.
- 1.3 Use of the "This Manufacturer Certifies That This Product Meets SFI Specification 36.2" logo/designation, the authorized artwork style, or conventional lettering by a manufacturer, on a subject product, is intended only to indicate that the manufacturer of the product has represented that they have submitted the product to the recommended tests, with positive results, in compliance with the standards established herein.
- 1.4 This SFI Specification requires a demonstration that the product of a manufacturer meets or exceeds the requirements when the manufacturer enters the program; and on a periodic basis thereafter. Any manufacturer may participate in the program by providing Drag Boat Capsule Canopy Material that meets or exceeds the SFI Specification 36.2 test standards, by complying with the requirements of the SFI Specification 36.2 program, and by signing a licensing agreement with the SFI Foundation, Inc.

- 1.5 Compliance with this specification is entirely voluntary. However, when a manufacturer provides Drag Boat Capsule Canopy Material in compliance with all requirements of the SFI Specification 36.2 and enters into the licensing agreement with the SFI Foundation, Inc., they may certify that compliance with such standards is in accordance with the guidelines established herein.
- 1.6 Manufacturers wishing to participate in the program, in addition to the other requirements of this specification, must label each of their products with the manufacturer's name, trademark or symbol as well as the date of manufacture of the product.
- 1.7 No manufacturer may display the SFI logo/designation on their product unless the manufacturer has signed a licensing agreement with SFI and has successfully complied with all the requirements of this specification and the self-certification program.

2.0 DEFINITIONS

- 2.1 Canopy: A transparent aerodynamically shaped shield and adjoining frame structure make up the "lid" portion of a drag boat capsule. The formed Drag Boat Capsule Canopy Material provides clear visibility and protection from water spray, etc. during boat operation.
- 2.2 Drag Boat Capsule Canopies shall be inspected every two (2) years by the certifying manufacturer for re-certification. When a unit is determined to be acceptable for continued service, a new conformance label marked with the inspection date shall be used. When the certifying manufacturer of the Drag Boat Capsule Shell is no longer in business, and no viable replacement manufacturer exists, then the governing drag boat race sanctioning body may inspect the Drag Boat Capsule Shell for re-certification. When a unit is determined to be acceptable for continued service, the sanctioning body may affix a new conformance label marked with the inspection date.

3.0 CONSTRUCTION

Drag Boat Capsule Canopy Material shall be polycarbonate sheet material with a minimum thickness of .500 inches before hot forming. Additional layers of acrylic, polyurethane, flow coat or clear coat may be bonded to the primary canopy material but cannot be used as part of the tensile or impact strength canopy test samples. The canopy manufacturer must supply certification that the original flat sheet material was .500 inches or greater thickness.

4.0 MODEL CLASSIFICATION

The major factors for model determination are material and material thickness. A variation of either of these parameters is considered a model change and must be tested to initial design requirements.

5.0 TESTING

The test samples shall be fully processed new Drag Boat Capsule Canopy Material which is representative of Drag Boat Capsule Canopy Material currently produced or to be produced.

5.1 TENSILE STRENGTH - CANOPY MATERIAL

Test in accordance with ASTM D638, Type III except for the variations stated below.

5.1.1 SAMPLES

The sample size is determined by using dimensions per ASTM D638 Figure 1.

5.1.2 APPARATUS

A standard tensile test machine shall be used. The machine shall be capable of applying the required tensile load of 20 inches/min. $\pm 10\%$ in accordance with Table 1, Designations for Speed of Testing per ASTM D638-91, and shall have adequate instrumentation to verify the test load.

5.1.3 CALIBRATION

The test machine shall also be in calibration and traceable to the National Bureau of Standards.

5.1.4 PROCEDURE

Record the physical dimensions of the test bars. For each sample, increase the tensile load until the test bar breaks. Record the load and elongation at appropriate points.

5.1.5 INTERPRET RESULTS

Determine tensile strength and elongation for each sample.

5.2 IZOD VALUE - CANOPY MATERIAL

Test in accordance with ASTM D256, Method A, except for the variations stated below.

5.2.1 SAMPLES

The sample size is determined by using dimensions per ASTM D256 Figure 4.

5.2.2 APPARATUS

A properly calibrated Cantilever Beam (Izod-Type) Impact Machine shall be used.

5.2.3 CALIBRATION

Accuracy of the test machine shall be in accordance with ASTM D256 Appendix X1.

5.2.4 PROCEDURE

Five samples shall be conditioned and tested at the temperature of 73°F ±4°F to determine the average impact value.

5.2.5 INTERPRET RESULTS

Calculate the average impact value.

6.0 PROOF OF COMPLIANCE

Drag Boat Capsule Canopy Material manufacturers are required to provide the following information to enroll in this program:

6.1 TENSILE STRENGTH - CANOPY MATERIAL

6.1.1 Material shall demonstrate minimum tensile strength of 8,800 psi.

6.1.2 Material shall demonstrate minimum elongation of 50%.

6.2 IMPACT STRENGTH - CANOPY MATERIAL

Material shall demonstrate minimum IZOD value of 1.75 ft lbs/in.

7.0 TEST REPORTS

A separate test report, or set of test reports if required, shall be submitted for each product model. If more than one test facility is required to complete all necessary tests, then a separate test report shall be submitted from each one. A test report shall be submitted for each component, if tested separately. The test facility shall assign a unique number to each test report. This number along with the report date and page number shall appear on each page. Each test report shall include:

7.1 RELEVANT INFORMATION

- 7.1.1 Manufacturer's name, contact name, address and telephone number.
- 7.1.2 Name, address and telephone number of the test facility.
- 7.1.3 Name and signature of the responsible test supervisor.
- 7.1.4 Actual date of the test.
- 7.1.5 Specification number and effective date.
- 7.1.6 Product name, description and model designation.
- 7.1.7 Component name and description.

7.2 TESTS

Each test conducted shall be listed showing the test name, apparatus used, procedure used and test results obtained along with any other appropriate information.

7.3 AUTHENTICATION

Test reports shall be authenticated and stamped by a Professional Engineer who is registered in the state in which the testing is conducted. If necessary, SFI may allow an equivalent entity to provide authentication.

8.0 INITIAL DESIGN VALIDATION

To receive initial recognition from SFI as a participant in the SFI Specification 36.2 Program, the manufacturer must submit to SFI all information delineated in the Proof of Compliance section. This information shall be provided for each Drag Boat Capsule model offered by the applicant that is to be included in the program. Any change in design, materials and/or methods of manufacturing not specifically excluded is considered a model change and, therefore, requires initial design validation.

9.0 PERIODIC REVALIDATION

Test reports with successful test results must be submitted to SFI at least once every 24 month period following the date of the initial design validation test for each model of Drag Boat Capsule Canopy Material manufactured by the participant. If multiple test reports are required to obtain all test results, then the earliest test date shall be used to determine when the periodic revalidation reports are due.

10.0 CERTIFICATION OF COMPLIANCE

Upon demonstration of successful compliance with all the requirements of the specification and the self-certification program and upon entering the licensing agreement with SFI, the manufacturer may advertise, present and offer Drag Boat Capsule Canopy Material for sale with the representation that their product meets the SFI Specification 36.2. Continuing certification is contingent upon the following additional considerations: (1) the product shall be resubmitted for testing following any change in design, materials and/or methods of manufacturing not specifically excluded, and (2) periodic revalidation test reports are submitted when due to SFI.

11.0 CONFORMANCE LABELS

The conformance label is a sticker. The serial number should appear on the customer invoice to aid in identification and tracking.

12.0 DECERTIFICATION

Participating manufacturers are subject to decertification when not in compliance with the requirements of this program or when their products are not in compliance with the requirements of this specification. Decertification will provide SFI the right to effect any and all remedies which are available to SFI in the licensing agreement.

13.0 APPEAL PROCEDURE

In the event of decertification, the manufacturer is entitled to an appeal of the decision of SFI. Requests for appeal must be received by SFI no later than thirty days following receipt of the notice of decertification. Appeals of such decisions will be heard at the next meeting of the Board of Directors of SFI.

14.0 STATEMENT OF LIMITATIONS

Testing procedures and/or standards contained in this specification are intended for use only as a guide in determining compliance with the minimum performance requirements as defined herein. The granting and assignment of the "This Manufacturer Certifies That This Product Meets SFI Specification 36.2" logo/designation is in no way an endorsement or certification of product performance or reliability by SFI. SFI, its officers, directors and/or members assume no responsibility, legal or otherwise, for failure or malfunctions of a product under this program.

15.0 COSTS

All costs involved in this program will be absorbed by the submitting manufacturer.

16.0 COMPLIANCE PERIOD

As this specification is revised to reflect changes in technology and/or field conditions, to remain current, participating manufacturers in the SFI Specification 36.2, Drag Boat Capsule Canopy Material, Program, must demonstrate full compliance with the requirements of this specification within ninety (90) days of the latest effective date.

*	Original Issue:	January 30, 1997
	Revised:	February 13, 1998
	Reviewed:	September 18, 1998
	Revised:	February 12, 2002
	Reviewed:	December 11, 2004
	Reviewed:	December 3, 2011
	Reviewed:	December 12, 2015
	Reviewed:	December 8, 2017
	Discontinued:	June 5, 2019